



# MOUNTAIN STATES ASPHALT INC.

## Mountain States Asphalt Certificate of Analysis

205 s Emerald Rd  
Tooele, UT 84074

Product	CSS-1H	Sample ID:	April	Date	4/19/2024
Test	Temp	Method	Specification	Result	
<b>Test</b>					
Residue, % by mass		AASHTO T59	Min. 57	58	
Storage Stability, 24 Hr., %		AASHTO T59	Max. 1	0	
Sieve, %		AASHTO T59	Max 0.10	0	
Cement Mixing, %		AASHTO T59	Max 2.0	0	
Particle Charge		AASHTO T59	Positive	+	
Saybolt Furol Viscosity, sec	25.0°	AASHTO T59	20-100	25	
<b>Distillation Residue</b>					
Penetration, 100g, 5sec	25.0°	AASHTO T49	40-90	72	
Solubility, %		AASHTO T44	Min 97.5	99.9	
Ductility (5cm/min.), cm	25.0°	AASHTO T51	Min. 40	60+	

\*Result from subcontractor

Notes: This sample complied with the requirements of UDOT Section 02745 and AASHTO M208.

Tested By:

  
Jameson Hulse, Binder Tech

Reviewed By:

  
Gene Chrisenbery, Vice President