



MOUNTAIN STATES ASPHALT INC.

205 s Emerald Rd
Tooele, UT 84074

SUPERPAVE™ Binder Grade:	PG 58-28	Date Recieved:	7/24/2024	By:	JH
Sample ID:	July				
Sample Condition (ie Good/Open):	Good	Date Tested:	7/24/2024	By:	JH
Test		Temp	Method	Specification	Result
ORIGINAL BINDER					
AASHTO M 320 Requirements					
Viscosity, Pa*s		135°C	T 316	3.0 max	0.375
Dynamic Shear	G*/sinδ, 10 rad./sec., kPa	58°C	T 315	1.0 min	0.46
RTFOT RESIDUE					
AASHTO M 320 Requirements					
Mass Change, % (Mass Loss is reported as Negative)			T 240	1.0 max	-0.071%
Dynamic Shear	G*/sinδ, 10 rad./sec., kPa	58°C	T 315	2.2 min	3.4
PRESSURE AGING RESIDUE (100°C, 300 psi, 20 hr.)					
AASHTO M 320 Requirements					
Dynamic Shear	G*(sinδ), 10 rad./sec., kPa	19°C	T 315	5,000 max	4775
Creep Stiffness	Stiffness, MPa (60 sec.)	-18°C	T 313	300 max	255
	m Value			0.300 min	0.336

*Result from subcontractor

Notes: This sample complied with the requirements of AASTHO Section M320, PG 58-28

Tested By:

Jameson Hulse, Binder Tech

Reviewed By:

Gene Chrisenbery, Vice President