



MOUNTAIN STATES ASPHALT INC.

205 s Emerald Rd
Tooele, UT 84074

SUPERPAVE™ Binder Grade:	PG 64-22	Date Sampled:	3/10/2025	By:	JH
Sample ID:	2025 Mix Design				
Sample Condition (ie Good/Open):	Good	Date Tested:	3/10/2025	By:	JH
Test		Temp	Method	Specification	Result
ORIGINAL BINDER					
AASHTO M 320 Requirements					
Viscosity, Pa*s		135°C	T 316	3.0 max	0.412
Dynamic Shear		G*/sinδ, 10 rad./sec., kPa	64°C	T 315	1.0 min 1.49
RTFOT RESIDUE					
AASHTO M 320 Requirements					
Mass Change, % (Mass Loss is reported as Negative)			T 240	1.0 max	-0.160%
Dynamic Shear		G*/sinδ, 10 rad./sec., kPa	64°C	T 315	2.2 min 3.48
PRESSURE AGING RESIDUE (100°C, 300 psi, 20 hr.)					
AASHTO M 320 Requirements					
Dynamic Shear		G*(sinδ), 10 rad./sec., kPa	25°C	T 315	5,000 max 3948
Creep Stiffness		Stiffness, MPa (60 sec.)	-12°C	T 313	300 max 187
		m Value			0.300 min 0.339

*Result from subcontractor

Tested By:

Jameson Hulse, Binder Tech

Reviewed By:

Gene Christenbery, Vice President